

BITUMEN 60/70

| | Specification | Test Method |
|-------------------------------------|---------------|------------------|
| Specific gravity @25/25 C | 1.01 - 1.06 | D-70 |
| Penetration@25 C | 60/70 | D-5 |
| Softening point C | 49/ 59 | D-36 |
| Ductility @25 C | 100 min | D- 113 |
| Loss on heating (wt)% | 0.2 max | D- 6 |
| Drop in penetration after heating % | 20 max | D- 6 & D- 5 |
| Flash point C | 250min | D-92 |
| Solubility in CS2 (wt)% | 99.5 min | D-4 |
| Spot test | negative | *A.A.S.H.O.T.102 |