

## EP-C 30 R

**1) Product Description:** The grade is a heterophasic polypropylene copolymer for injection molding the product offers an excellent balance of stiffness.

**2) Application:**

- Automotive parts, wells, garden furniture, chair shells and stadium seats.

**3) Typical data. (Table)**

Property	Unit	Typical Value	Test Method
MFI	Dg/min	7.0	ISO 1133
Density	g/cm <sup>3</sup>	0.9	ISO 1183
Flexural Modulus	N/mm <sup>2</sup>	1150	ISO 178
Tensile	N/mm <sup>2</sup>	26	ISO R527
Elongation	%	10	ISO R527
Izod Impact	Kj/m <sup>2</sup>	8	ISO 180
Hardness	point	68	ISO 868
Vicat	°C	151	ISO 306/A
H.D.T	°C	88	ISO 75/B

\* Typical Values : not to be construed as specifications

Producer: Marun Petrochemical Co. Licensor: Basell Packing: 25 Kg plastic bag